

# 80S-Ni1 Carbon Steel Welding Wire and Rod

U.S. ALLOY CO.  
 dba Washington Alloy  
 7010-G Reames Rd.  
 Charlotte, NC 28216  
[www.weldingwire.com](http://www.weldingwire.com)



**American Welding Society**  
 Sustaining Company Member



## ALLOY DESCRIPTION AND APPLICATION;

80S-Ni-1 is for welding fine grained and low alloy nickel steels producing high impact values even at low temperature such as -50° F.

### TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit <sup>(1)</sup> 98Ar/2%O<sub>2</sub>

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Travel speed (ipm)	CO <sub>2</sub> (cfh)
0.023	80-350	30-85	14-19	10-15	20-25
0.030	110-340	40-130	15-20	12-24	20-25
0.035	100-520	60-235	16-25	11-40	20-30
0.045	70-270	90-290	18-23	12-22	25-35
<i>Spray 0.035</i>	<i>320-600</i>	<i>160-300</i>	<i>23-26</i>	<i>11-22</i>	<sup>(1)</sup> <i>25-35</i>
<i>0.045</i>	<i>170-550</i>	<i>170-375</i>	<i>23-29</i>	<i>12-21</i>	<sup>(1)</sup> <i>25-35</i>
<i>1/16"</i>	<i>175-350</i>	<i>275-475</i>	<i>25-31</i>	<i>9-19</i>	<sup>(1)</sup> <i>25-35</i>

### TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	100-160	12	3/8"	20	1/16-3/32"
1/16-3/32"	3/32"	120-250	12	3/8"	20	1/8- 3/16"
1/8"	1/8"	150-300	12	1/2"	25	1/4-1/2"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

### TYPICAL WIRE CHEMISTRY (%) AND WELD METAL PROPERTIES; 100%CO<sub>2</sub>

	AWS Spec.		AWS Spec.
Carbon	0.12 max.	Nickel	0.80-1.10
Manganese	1.25	Chromium	0.15 max.
Silicon	0.40-0.80	Vanadium	0.05 max.
Phosphorus	0.025 max.	Tensile Strength (psi)	80,000 min
Sulfur	0.025 max.	Yield Strength (psi)	68,000 min.
Molybdenum	0.35 max.	Elongation in 2"	24% min.
Copper contents and coating	0.35 max.	Charpy V-notch at -50°F	20 ft-lbs min.

**AVAILABLE SIZES:** TC 80S-Ni1 = Spools of .035, .045, 1/16  
 TT 80S-Ni1 = Cut lengths of .045, 1/16, 3/32, 1/8,



### SPECIFICATIONS; ANSI/AWS A5.28 ER 80S-Ni1

**EAST COAST**  
 7010-G Reames Rd  
 Charlotte, NC 28216  
 Tel (888) 522-8296  
 Fax (704)598-6673

**GULF COAST**  
 4755 Alpine Drive #100A  
 Stafford, TX 77477  
 Tel (877) 711-9274  
 Fax (281)313-6332

**WEST COAST**  
 8535 Utica Ave  
 Rancho Cucamonga, CA 91730  
 Tel(800)830-9033  
 Fax (909)291-4586

2012 DC

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.