



WASHINGTON ALLOY'S Quality Management System is Certified to ISO 9001:2008 Cert # 05-R0925

USA 90S-B3 Welding Wire and Rod

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION;

90S-B3 is a low alloy filler designed to produce high strengths on 2 1/4 & Cr -1 Mo steels found in high temperature/high pressure piping and vessels. May also be used on carbon steels to Cr-Mo base metals. Controlled preheat, interpass and postheat treatment may be needed to avoid cracking.

TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit ⁽¹⁾ 98Ar/2% O₂

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Travel speed (ipm)	75/25 CO ₂ (cfh)
0.023	80-350	30-85	14-19	10-15	20-25
0.030	110-340	40-130	15-20	12-24	20-25
0.035	100-520	60-235	16-25	11-40	20-30
0.045	70-270	90-290	18-23	12-22	25-35
<i>Spray 0.035</i>	<i>320-600</i>	<i>160-300</i>	<i>23-26</i>	<i>11-22</i>	⁽¹⁾ <i>25-35</i>
<i>0.045</i>	<i>170-550</i>	<i>170-375</i>	<i>23-29</i>	<i>12-21</i>	⁽¹⁾ <i>25-35</i>
<i>1/16"</i>	<i>175-350</i>	<i>275-475</i>	<i>25-31</i>	<i>9-19</i>	⁽¹⁾ <i>25-35</i>

TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	100-160	12	3/8"	20	1/16-3/32"
1/16-3/32"	3/32"	120-250	12	3/8"	20	1/8- 3/16"
1/8"	1/8"	150-300	12	1/2"	25	1/4-1/2"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

WIRE CHEMISTRY (%) AND WELD METAL PROPERTIES;

	AWS Spec.	90S-B3		AWS Spec	Typical
Carbon	0.07-0.12	0.10	Tensile Strength (psi)	90,000 min.	94,500
Manganese	0.40-0.70	0.63	Yield Strength (psi)	78,000 min.	80,500
Silicon	0.40-0.70	0.46	Elongation in 2"	17% min.	19%
Phosphorus	0.025 max	0.012			
Sulfur	0.025 max	0.012			
Molybdenum	0.90-1.20	1.06	Nickel	0.20 max	0.10
Chromium	2.30-2.70	2.55	Copper	0.35 max	0.11

AVAILABLE SIZES: TC = Spools and rods of .030, .035, .045, 1/16,
TT = Cut lengths of .045, 1/16, 3/32, 1/8, 5/32

Other sizes available – please inquire

SPECIFICATIONS; ANSI/AWS A5.28 ER 90S-B3
ASME SFA 5.28 ER 90S-B3 ; A-4, F-6

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

GULF COAST
4755 Alpine Drive #100A
Stafford, TX 77477
Tel (877) 711-9274
Fax (281)313-6332

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



2012 DC

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.