



Quality Management System
in accordance with
ISO 9001
Cert # 05-R0925

Alloy 82 Welding Parameters

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



Washington Alloy 82 is a nickel-chromium-iron filler metal used for MIG, TIG, submerged arc and plasma arc welding of nickel base Inconel® 600, 601 and 690 as well as Incoloy® 330,

800 and 800 HT to themselves or to carbon steel, stainless steel, high nickel base 200 and to nickel-copper Monel® 400. Washington Alloy 82 can also be used for joining high nickel base 200 to stainless steel, nickel-copper Monel® 400 to carbon steel and for overlaying on steel. Used for welding of ASTM B163, B166, B167 and also B168 having UNS N06600.

TYPICAL GMAW WELDING PROCEDURES; DCEP Spray Arc

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stick-out	Argon (cfh)
0.030	550-750	175-250	26-32	3/8-1/2"	30-40
0.035	425-575	175-300	26-32	3/8-1/2"	30-40
0.045	250-350	200-310	26-32	3/8-1/2"	35-50
0.062	125-200	250-330	27-33	1/2"-5/8"	35-50

TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit (cfh)

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stick-out	75Ar/25He
0.035	150-200	90-110	19-21	3/8-1/2"	35-45
0.045	175-225	100-140	22-24	3/8-1/2"	40-50

TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	80-150	12	1/2"	20	1/16-1/8"
3/32"	3/32"	150-250	12	3/4"	25	1/8- 3/16"
1/8"	1/8"	200-375	12	5/8"	30	1/4-1/2"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

AWS CHEMISTRY REQUIREMENTS (%) & TYPICAL WELD METAL STRENGTHS;

Carbon	0.10 max	Tensile Strength (psi)	80,000
Manganese	2.50 – 3.50	Yield Strength (psi)	40,000
Iron	3.00 max	Elongation	30%
Phosphorus	0.030 max		
Sulphur	0.015 max	Niobium (or Cb) + Tantalum	2.0-3.0
Silicon	0.50 max	Cobalt max if specified	0.12
Copper	0.50 max	Chromium	18.0-22.0
Nickel + Co	67.0 min.	Titanium	0.75 max

AVAILABLE SIZES: TN 82 = Spools of 030, 035, 045, 1/16,
TN 82/ = Cut lengths of 030, 035, 045, 1/16, 3/32, 1/8, 5/32
Other sizes available – please inquire

SPECIFICATIONS; ANSI/AWS A5.14 ERNiCr-3
ASME SFA 5.14 ERNiCr-3

EAST COAST 7010-G Reames Rd Charlotte, NC 28216 Tel (888) 522-8296 Fax (704)598-6673	GULF COAST 4855 Alpine Drive #190 Stafford, TX 77477 Tel (877) 711-9274 Fax (281)313-6332	WEST COAST 8535 Utica Ave Rancho Cucamonga, CA 91730 Tel(800)830-9033 Fax (909)291-4586
---	--	--



Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.