



# Nickel Aluminum Bronze Welding Wire and Rod

U.S. ALLOY CO.  
dba Washington Alloy  
7010-G Reames Rd.  
Charlotte, NC 28216  
[www.weldingwire.com](http://www.weldingwire.com)

Quality Management System  
in accordance with  
**ISO 9001**  
Cert # 05-R0925



## ALLOY DESCRIPTION AND APPLICATION;

Washington Alloy Nickel-Aluminum Bronze filler metal is used for MIG and TIG welding of cast and wrought nickel-aluminum bronze parts such as ship propellers, where high resistance to corrosion, erosion and cavitations in salt or brackish water is required. Nickel-Aluminum Bronze is a very popular filler metal in offshore technology for such items as sea-water desalting, shipbuilding and repair. Also used in the power plant and chemical industry for pumps and tube systems. Helium may be preferred when TIG welding on Al-bronzes that has 300°F maximum interpass recommendations.

## TYPICAL GMAW WELDING PROCEDURES; DCEP Spray transfer

| Wire Diameter | Wire Speed (ipm) | Amps    | Volts | Argon (cfh) |
|---------------|------------------|---------|-------|-------------|
| 0.023         | 460-580          | 60-120  | 21-22 | 20-25       |
| 0.030         | 450-525          | 130-160 | 21-24 | 20-30       |
| 0.035         | 385-455          | 155-190 | 23-25 | 25-30       |
| 0.045         | 275-310          | 210-235 | 26-28 | 30-35       |
| 1/16          | 150-240          | 250-310 | 27-31 | 35-40       |

## TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

| Filler Wire Size | Tungsten | Amps    | Volts | Gas Cup Size | Argon (cfh) | Base thickness |
|------------------|----------|---------|-------|--------------|-------------|----------------|
| 1/16"            | 1/16"    | 80-170  | 12    | 3/8-1/2"     | 20          | 1/16-1/8"      |
| 3/32"            | 3/32"    | 140-275 | 12    | 3/8-1/2"     | 20          | 1/8- 3/16"     |
| 1/8"             | 1/8"     | 200-375 | 12    | 1/2"         | 25          | 1/4-3/8"       |
| 1/8-5/32"        | 3/16"    | 260-475 | 12    | 1/2-3/4"     | 30          | 3/8-1/2"       |

Procedures may vary with change in position, base metals, filler metals, equipment and other changes. Copper base may need preheat and high side of range, Bronze base may need preheat and mid-high side of range, Steels preheat per carbon content

## CHEMICAL COMPOSITION REQUIRMENT (%) AND PHYICAL PROPERTIES;

|           |           |                                |            |
|-----------|-----------|--------------------------------|------------|
| Zinc      | 0.02      | Solidus                        | 1904° F    |
| Iron      | 3.0-5.0   | Liquidus                       | 1940°F     |
| Silicon   | 0.10      | Density (lbs/in <sup>3</sup> ) | 0.275      |
| Aluminum  | 8.5-9.5   | Thermal Conductivity           | 37.0 Btu   |
| Lead      | 0.02      | Brinell Hardness               | 160-200    |
| Copper    | Remainder | Elongation                     | 23 %       |
| Manganese | 0.60-3.50 | Tensile Strength (psi)         | 72-140,000 |
| Nickel    | 4.0-5.5   | Yield Strength (psi)           | 35-60,000  |

All single values on composition are maximum percentages & Total others elements 0.50

**AVAILABLE SIZES:** TCU CU-NI-AL = Spools of .035, .045, 1/16  
TCU CU-NI-AL/ Cut lengths of .045, 1/16, 3/32, 1/8, 5/32  
Other sizes available – please inquire

**SPECIFICATIONS;** ANSI/AWS A5.7 ERcUNiAl  
ASME SFA 5.7 ERcUNiAl

| EAST COAST          | GULF COAST              | WEST COAST                 |
|---------------------|-------------------------|----------------------------|
| 7010-G Reames Rd    | 4755 Alpine Drive #100A | 8535 Utica Ave             |
| Charlotte, NC 28216 | Stafford, TX 77477      | Rancho Cucamonga, CA 91730 |
| Tel (888) 522-8296  | Tel (877) 711-9274      | Tel(800)830-9033           |
| Fax (704)598-6673   | Fax (281)313-6332       | Fax (909)291-4586          |



10-2010 DC

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.