



Quality Management System
in accordance with
ISO 9001:2000
Cert # 05-R0925

1100 ALUMINUM Welding wire

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION;

1100 is a 99% aluminum filler recommended for welding of 1100, 1060, 1080, 1350, 3003, and similar base metals.

TYPICAL GMAW WELDING PROCEDURES; DCEP

Wire Diameter	Amps	Volts	Travel speed (ipm)	Argon (cfh)
0.030	60-175	15-24	25-45	25-30
0.035	70-185	15-27	25-40	30-35
3/64	125-260	20-29	24-35	35-45
1/16	170-300	24-30	28-38	45-55
3/32	275-400	26-31	14-20	60-75

TYPICAL GTAW WELDING PROCEDURES; ACHF with Pure or Ziconiated

Hemisphere shape tungsten tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	60-80	15	3/8"	20	1/16"
3/32"	3/32"	125-160	15	3/8"	20	1/8"
1/8"	1/8"	190-220	15	7/16"	20	3/16"
5/32"	5/32"	200-300	15	1/2"	25	1/4"
3/16"	3/16"	330-380	15-20	5/8"	25	3/8"
1/4"	1/4"	400-450	25	5/8"	25	1/2"

Procedures are base on flat position and may vary with change in position, base metals, filler metals, equipment and other changes.

TYPICAL CHEMISTRY AND PROPERTIES;

Silicon & Iron 0.95	Copper 0.05-0.20	Manganese 0.05	Zinc 0.10	Beryllium 0.0008
Aluminum Remainder and others each 0.50 & total 0.15		All values are maximum percentage unless noted		

Solidus:1090°F Liquidus:1215°F Density: 0.098 lbs./cu. In. Anodize color: Slight golden
Average Tensile Strength All weld metal (as welded) 13,500 psi (93 mpa)

AVAILABLE SIZES: TA 1100= Spools of .030, .035, 3/64, 1/16, 3/32
TB 1100 = Cut lengths of .030, .035, 3/64, 1/16, 5/64, 3/32, 1/8, 3/16, 1/4
Other sizes available – please inquire

SPECIFICATIONS; ANSI/AWS A5.10 ER/R 1100
 ASME SFA5.10 ER/R 1100

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



8-2005 DC

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.