



Quality Management System
in accordance with
ISO 9001:2000
Cert # 05-R0925

SUPERFLOW[®] 0 BRAZING ALLOY

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION:

SUPERFLOW[®] 0 is a Phos-copper brazing alloy formulated to join copper, brass and bronze. This alloy is commonly used where there is a close or controlled fit up. *Superflow* brazing flux is needed when working on brazeable grades brass or bronze. Phos-Copper alloys are self-fluxing on copper but should not be used, on copper alloys containing more than 10% nickel, steels, and ferrous metals or in any sulfurous atmospheres. Aluminum bronze requires the use of Aluminum bronze brazing flux.

CHEMICAL COMPOSITION, Weight Percent:

Phosphorus	7.0-7.5
Copper	Balance
Total Others Elements	0.15

PHYSICAL DATA:

Solidus	1310°F (710°C)
Liquidus	1460°F (793°C)
Brazing Range	1350-1500°F (732-816°C)
Color	Bright Copper
Specific Gravity	8.13
Density (lb/cu in.)	0.287
Electrical Conductivity (% of IACS)	8.5
Electrical Resistivity (Microhm-cm)	21.5

AVAILABLE SIZES:

TAG 0 = 20" Rods of 1/16, 3/32, 1/8 X .050
36" Rods of 3/32, 1/8, 3/16, 1/4
Spools of 1/16
Other sizes available – please inquire

SPECIFICATIONS:

AWS A5.8/A5.8M	BCuP-2
ASME SFA5.8	BCuP-2
FED QQ-B-650C	BCuP-2

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



DC 5-2006

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations and decisions and should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damaged incurred from the use of any information contained herein, in whole or in part.