



Quality Management System
in accordance with
ISO 9001:2000
Cert # 05-R0925

SUPERFLOW[®] 15 BRAZING ALLOY

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION:

SUPERFLOW[®] 15 is a Phos-copper brazing alloy formulated to join copper, brass and bronze. This alloy is the standard of the industry for many air conditioning and refrigeration applications as well as electrical. *Superflow* brazing flux is needed when working on brazeable grades brass or bronze. Phos-Copper alloys are self-fluxing on copper but should not be used, on copper alloys containing more than 10% nickel, steels, and ferrous metals or in any sulfurous atmospheres. Aluminum bronze requires the use of Aluminum bronze brazing flux.

CHEMICAL COMPOSITION, Weight Percent:

Silver	14.5-15.5
Copper	Balance
Phosphorus	4.8-5.2
Total Others Elements	0.15

PHYSICAL DATA:

Solidus	1190°F (643°C)
Liquidus	1475°F (802°C)
Brazing Range	1300-1500°F (704-816°C)
Color	Bright Silver Copper
Specific Gravity	8.44
Density (lb/cu in.)	0.301
Electrical Conductivity (% of IACS)	9.91
Electrical Resistivity (Microhm-cm)	17.38

AVAILABLE SIZES:

TAG 15 = 20" Rods of 1/16, 1/8 X .050
36" Rods of 5/64, 3/32, 1/8, 3/16,
36" Square rods of 1/8 & 1/4
Other sizes available – please inquire

SPECIFICATIONS:

AWS A5.8/A5.8M	BCuP-5
ASME SFA5.8	BCuP-5
FED QQ-B-650C & QQ-B-654A	BCuP-5
FED QQ-B-654 & MIL -B-15395	Grade III

EAST COAST

7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

WEST COAST

8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



dc5-2006

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations and decisions and should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damaged incurred from the use of any information contained herein, in whole or in part.