



71T-1C Carbon Steel Flux-Cored Wire

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com

Quality Management System
in accordance with
ISO 9001:2000
Cert # 05-R0925



ALLOY DESCRIPTION AND APPLICATION:

71T-1C is a flux cored wire designed for single or multi pass welding having a smooth arc transfer, low spatter, flat to slightly convex bead contour, with a high deposition rate and easily removal slag. This all-position wire has excellent feeding and low fume generation using 100% CO₂ making it a good choice for mild steel and higher strengths steels. Argon - CO₂ gases may be used if tested with application.

TYPICAL FCAW WELDING PROCEDURES; DCEP OPTIMUM IN BOLD (FLAT)

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stickout	CO ₂ (cfh)
0.035	275- 580 -780	130- 200 -260	23- 27 -30	3/8-3/4"	35-40
0.045	200- 450 -600	150- 250 -335	22- 29 -33	1/2-1"	35-45
0.052	150- 400 -600	140- 275 -390	19- 28 -35	1/2-1"	40-50
1/16"	150- 330 -490	150- 330 -475	23- 30 -38	1/2-1"	40-50
5/64"	120- 250 -300	250- 385 -450	26- 29 -32	3/4-1 1/4"	40-50
3/32"	110- 185 -275	300- 425 -550	25- 29 -34	3/4-1 1/4"	40-50

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

TYPICAL WELD METAL CHEMISTRY (%) AND WELD METAL PROPERTIES;

	AWS Spec.	U.S. ALLOY 71T-1C	BASED ON 100% CO ₂	AWS Spec	Typical
Carbon	0.12 max	0.03			
Manganese	1.75 max	1.48	Tensile Strength (psi)	70-95,000	89,000
Silicon	0.90 max	0.75	Yield Strength (psi)	58,000 min.	80,000
Phosphorus	0.030 max.	0.012	Elongation in 2"	22 % min.	28%
Sulfur	0.030 max.	0.009	Charpy V-notch at 0°F	20 ft-lbs min.	48 ft-lbs
Copper	0.35 max.	0.022			
Nickel	0.50 max.	0.030	Chromium	0.20 max.	0.039
Molybdenum	0.30 max.	0.010	Vanadium	0.08 max.	0.020

AVAILABLE SIZES: TCF 71T-1= Spools of .035, .045, .052, 1/16, 3/32

SPECIFICATIONS; ANSI/AWS A5.20 E71T-1C
ASME SFA A5.20 E71T-1C

(Formerly classified as E71T-1)

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



5-2006 DC

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part .