



# 71T-1LF Carbon Steel Flux-Cored Wire

U.S. ALLOY CO.  
dba Washington Alloy  
7010-G Reames Rd.  
Charlotte, NC 28216  
[www.weldingwire.com](http://www.weldingwire.com)

Quality Management System  
in accordance with  
**ISO 9001:2000**  
Cert # 05-R0925



## ALLOY DESCRIPTION AND APPLICATION:

71T-1 LF is a flux cored wire designed for single or multi pass welding having a smooth arc transfer, low spatter, flat to slightly convex bead contour, with a high deposition rate and easily removal slag. This all-position wire has excellent feeding and **low fume** generation using 100% CO<sub>2</sub> making it a good choice for mild steel and higher strengths steels. Argon - CO<sub>2</sub> gases may be used if tested with application.

## TYPICAL FCAW WELDING PROCEDURES; DCEP OPTIMUM IN BOLD (FLAT)

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Electrical Stickout	CO <sub>2</sub> (cfh)
0.035	275- <b>580</b> -780	130- <b>200</b> -260	23- <b>27</b> -30	3/8-3/4"	35-40
0.045	200- <b>450</b> -600	150- <b>250</b> -335	22- <b>29</b> -33	1/2-1"	35-45
0.052	150- <b>400</b> -600	140- <b>275</b> -390	19- <b>28</b> -35	1/2-1"	40-50
1/16"	150- <b>330</b> -490	150- <b>330</b> -475	23- <b>30</b> -38	1/2-1"	40-50
5/64"	120- <b>250</b> -300	250- <b>385</b> -450	26- <b>29</b> -32	3/4-1 1/4"	40-50
3/32"	110- <b>185</b> -275	300- <b>425</b> -550	25- <b>29</b> -34	3/4-1 1/4"	40-50

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

## TYPICAL WELD METAL CHEMISTRY (%) AND WELD METAL PROPERTIES;

	AWS Spec.	U.S. ALLOY 71T-1LF	BASED ON 100% CO <sub>2</sub>	AWS Spec	Typical
Carbon	0.12 max	0.03			
Manganese	1.75 max	1.45	Tensile Strength (psi)	70-95,000	80,000
Silicon	0.90 max	0.30	Yield Strength (psi)	58,000 min.	74,000
Phosphorus	0.030 max.	0.015	Elongation in 2"	22 % min.	28%
Sulfur	0.030 max.	0.010	Charpy V-notch at 0°F	20 ft·lbs min.	44 ft·lbs

**AVAILABLE SIZES:** TCF 71T-1= Spools of .035, .045, .052, 1/16, 3/32

**SPECIFICATIONS; ANSI/AWS A5.20** E71T-1C, E71T-1M  
**ASME SFA A5.20** E71T-1C, E71T-1M  
( Formerly classified as E71T-1 )

**EAST COAST**  
7010-G Reames Rd  
Charlotte, NC 28216  
Tel (888) 522-8296  
Fax (704)598-6673

**WEST COAST**  
8535 Utica Ave  
Rancho Cucamonga, CA 91730  
Tel(800)830-9033  
Fax (909)291-4586



8-2006 DC

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.