



Quality Management System
in accordance with
ISO 9001:2000
Cert # 05-R0925

SUPERFLOW[®] 50N CF BRAZING ALLOY

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION:

SUPERFLOW[®] 50N CF is a cadmium free silver brazing alloy with nickel and the lowest working temperature in the cad-free nickel family which has great flow, wetting, ductility, penetration. *SUPERFLOW 50N CF* is commonly used to join any combinations of copper, brass, steel, bronze, carbide tips and stainless steel. The addition of nickel improves the corrosion needed with stainless and nickel alloys while minimizing stress corrosion cracking as well as interface corrosion.

CHEMICAL COMPOSITION, Weight Percent:

Silver	49.0-51.0
Copper	19.0-21.0
Zinc	26.0-30.0
Nickel	1.5-2.5
Total Others Elements	0.15

PHYSICAL DATA:

Solidus	1220°F (660°C)
Liquidus	1305°F (707°C)
Brazing Range	1305-1550°F (707-843°C)
Color	White-Yellow to light gold
Specific Gravity	9.17
Density (Troy oz./cu in.)	4.80
Electrical Conductivity (% of IACS)	18.5
Electrical Resistivity (Microhm-cm)	11.85

AVAILABLE SIZES:

TAG 50NCF = Troy Ounce Coils and Rods of .030, .045, 3/64, 1/16,
TAG 50NCF = Flux Coat Rods of 1/16
Other sizes available – please inquire

SPECIFICATIONS:

AWS A5.8/A5.8M	BAG-24
ASME SFA5.8	BAG-24
AMS	4788

EAST COAST
7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

WEST COAST
8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



DC 5-2006

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations and decisions and should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damaged incurred from the use of any information contained herein, in whole or in part .