



Quality Management System  
in accordance with  
**ISO 9001:2000**  
Cert # 05-R0925

# SUPERFLOW<sup>®</sup> 56 CF BRAZING ALLOY

U.S. ALLOY CO.  
dba Washington Alloy  
7010-G Reames Rd.  
Charlotte, NC 28216  
[www.weldingwire.com](http://www.weldingwire.com)



## ALLOY DESCRIPTION AND APPLICATION:

*SUPERFLOW<sup>®</sup> 56 CF* is a cadmium free silver brazing alloy with a narrow melting range and the lowest working temperature in the cad-free family yielding premium flow, wetting, ductility, penetration. *SUPERFLOW 56CF* is commonly used to join any combinations of copper, brass, steel, bronze and stainless steel. This alloy is a great choice for food handling equipment and color match on stainless and nickel alloys while minimizing stress corrosion cracking.

## CHEMICAL COMPOSITION, Weight Percent:

Silver	55.0-57.0
Copper	21.0-23.0
Zinc	15.0-19.0
Tin	4.5-5.5
Total Others Elements	0.15

## PHYSICAL DATA:

Solidus	1145°F (618°C)
Liquidus	1205°F (652°C)
Brazing Range	1205-1400°F (652-760°C)
Color	White to light gold
Specific Gravity	9.47
Density (Troy oz./cu in.)	5.00
Electrical Conductivity (% of IACS)	20.5
Electrical Resistivity (Microhm-cm)	9.58

## AVAILABLE SIZES:

TAG 56CF = Troy Ounce Coils and Rods of .030, .045, 3/64, 1/16, 3/32, 1/8

TAG 56CF = Flux coated rods of 1/16, 3/32, 1/8

Other sizes available – please inquire

## SPECIFICATIONS:

<b>AWS</b> A5.8/A5.8M	BAG-7
<b>ASME</b> SFA5.8	BAG-7
<b>FED</b> QQ-B-654	BAG-7

EAST COAST  
7010-G Reames Rd  
Charlotte, NC 28216  
Tel (888) 522-8296  
Fax (704)598-6673

WEST COAST  
8535 Utica Ave  
Rancho Cucamonga, CA 91730  
Tel(800)830-9033  
Fax (909)291-4586



DC 5-2006

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations and decisions and should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damaged incurred from the use of any information contained herein, in whole or in part.