



ISO 9001:2000

70S-3 Carbon Steel Welding Wire and Rod

U.S. ALLOY CO.
dba Washington Alloy
7010-G Reames Rd.
Charlotte, NC 28216
www.weldingwire.com



ALLOY DESCRIPTION AND APPLICATION;

70S-3 is commonly a copper coated carbon steel that contains well balance levels of manganese and silicon which permits the use of CO₂ and also Argon –Oxygen shielding gases. Yielding almost a slag free quality weld deposit on most steels it provides an excellent welder satisfaction for post weld clean up. Some typical application includes auto frames, sheet metal, ships, barges, railcars, trailers, ornamental iron, furniture storage bins, earthmoving and farm equipment.

TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit ⁽¹⁾ 98Ar/2O₂

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Travel speed (ipm)	CO ₂ (cfh)
0.023	80-350	30-85	14-19	10-15	20-25
0.030	110-340	40-130	15-20	12-24	20-25
0.035	100-520	60-235	16-25	11-40	20-30
0.045	70-270	90-290	18-23	12-22	25-35
<i>Spray 0.035</i>	<i>320-600</i>	<i>160-300</i>	<i>23-26</i>	<i>11-22</i>	<i>(1)25-35</i>
<i>0.045</i>	<i>170-550</i>	<i>170-375</i>	<i>23-29</i>	<i>12-21</i>	<i>(1)25-35</i>
<i>1/16"</i>	<i>175-350</i>	<i>275-475</i>	<i>25-31</i>	<i>9-19</i>	<i>(1)25-35</i>

TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	100-160	12	3/8"	20	1/16-3/32"
1/16-3/32"	3/32"	120-250	12	3/8"	20	1/8- 3/16"
1/8"	1/8"	150-300	12	1/2"	25	1/4-1/2"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

TYPICAL WIRE CHEMISTRY (%) AND WELD METAL PROPERTIES; 100%CO₂

	AWS Spec.	70S-3		AWS Spec	Typical
Carbon	0.06-0.15	0.10	Tensile Strength (psi)	60,000 min.	62,400
Manganese	0.90-1.40	1.00	Yield Strength (psi)	70,000 min.	75,500
Silicon	0.45-0.75	0.55	Elongation in 2"	22% min.	30.7%
Phosphorus	0.025 max.	0.012	Charpy V-notch at 0°F	20 ft-lbs min.	66 ft-lbs
Sulfur	0.035 max.	0.012	Reduction of area	n/a	59%
Copper contents and coating	0.5 max.		Average Brinell Hardness	n/a	130

AVAILABLE SIZES: TC 70S-3 = Spools of .023, .030, .035, .045, .052

TT 70S-3 = Cut lengths of .030, .035, .045, 1/16, 3/32, 1/8, 5/32

Drums (PAIL PACK) and Other sizes available – please inquire

SPECIFICATIONS; ANSI/AWS A5.18 ER 70S-3

ASME SFA 5.18 ER 70S-3

EAST COAST

7010-G Reames Rd
Charlotte, NC 28216
Tel (888) 522-8296
Fax (704)598-6673

WEST COAST

8535 Utica Ave
Rancho Cucamonga, CA 91730
Tel(800)830-9033
Fax (909)291-4586



3-2006 DC

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part .